

A Review Paper Study on Stone Matrix Asphalt Using Banana Fibre

¹Chikkanagouda Choudhari, ²Pratiksha Malviya

¹M. Tech. Scholar, ²Professor Department of Civil Engineering

Millennium Institute of Technology, Bhopal, India

Abstract-In this present study comparison of strength of pavement wearing coat made with SMA mix with Banana fiber and without Banana fiber was done. World is as of now concentrating on alternate material sources that are environment agreeable and biodegradable in nature. Because of the expanding natural concerns, bio composite produced out of regular fiber and polymeric resin. All the research work done before by using banana fibers. Banana fibers are extensively used in SMA in Europe and USA. Stone Matrix Asphalt having good stability, strength and maintenance of smooth surface of roads & other structure is required. Stone Matrix Asphalt mix is prepared by blending of coarse and fine aggregates. Banana fibers improve service properties of SMA Mix by forming micromesh.

Keywords-Banana Fiber, Natural Aggregate, Binder content, SMA, HMA, Marshall Test.

I. INTRODUCTION

Stone Matrix Asphalt (SMA) is a gap-graded mixture, have a better stone to stone contact which gives better strength to the mixture.

In this research work aggregate used as per the MORTH specification which was taken from a same lot. The samples are made with aggregate with different gradation, filler (cement) and binder (bitumen 60/70). Fibers are used as stabilizer and are used to decrease the drain down and to increase the strength and stability of the SMA mix. The test of the SMA Mix samples is done in Marshall apparatus. Here the comparison of SMA Mix with and without banana fiber was done.

All the research work done before by using banana fibers. Banana fibers are extensively used in SMA in Europe and USA. These fibers are patented. The fibers improve the service properties of the mix by forming micromesh in the asphalt mix to prevent the drain down of the asphalt so as to increase the stability and durability of the mix. Here we have tried to use banana fiber which is more economic than cellulose fibers, doing same work as cellulose fiber.

Flexible pavements designing are preferred always over all other rigid pavements for road construction. Stone matrix asphalt mix sample were tested in Marshall Apparatus. SMA Mix is desired to have quality of resistance to wear & tear, greater strength for better performs during heavy loads.

Stone Matrix Asphalt (SMA)

Stone matrix asphalt (SMA), sometimes called stone mastic asphalt, is a gap-graded HMA originally developed in Europe to maximize rutting resistance and durability in heavy traffic

road. SMA has a high coarse aggregate content that interlocks to form a stone skeleton that resists permanent deformation. The stone skeleton is filled with a mastic of bitumen and filler to which fibers are added to provide adequate stability of bitumen and to prevent drainage of binder during transport and placement. Typical SMA composition consists of 70–80% coarse aggregate, 8–12% filler, 6.0–7.0% binder, and 0.3 per cent fiber. The deformation resistant capacity of SMA stems from a coarse stone skeleton providing more stone-on-stone contact than with conventional dense graded asphalt (DGA) mixes. Improved binder durability is a result of higher bitumen content, a thicker bitumen film, and lower air voids content. This high bitumen content also improves flexibility. Addition of a small quantity of cellulose or mineral fiber prevents drainage of bitumen during transport and placement. There are no precise design guidelines for SMA mixes. The essential features, which are the coarse aggregate skeleton and mastic composition, and the consequent surface texture and mixture stability, are largely determined by the selection of aggregate grading and the type and proportion of filler and binder. SMA improved rut resistance and durability. It has good fatigue and tensile strength. SMA is almost exclusively used for surface courses on high volume roads. Materials used for SMA are Gap- graded aggregate, modified asphalt binder, fiber filler. Other SMA benefits include wet weather friction (due to a coarser surface texture), lower tire noise (due to a coarser surface texture) and less severe reflective cracking. Mineral fillers and additives are used to minimize asphalt binder drain-down during construction, increase the amount of asphalt binder used in the mix and to improve mix durability.

II. LITERATURE SURVEY

This chapter presents the characteristics of SMA with fibers to justify research aim and sets the background for the proposed work.

Bradelyet.al. (2004) studied Utilization of waste fibers in

stone matrix asphalt mixtures. They used carpet, tire and polyester fibers to improve the strength and stability of mixture compared to cellulose fiber. They found no difference in moisture susceptibility and permanent deformation in SMA mix containing waste fibers as compared to SMA mix containing cellulose or mineral fiber.[4]

Kamaraj C., G. Kumar, G. Sharma, P.K. Jain and K.V. Babu (2004) carried laboratory study using natural rubber powder with 80/100 bitumen in SMA by wet process as well as dense graded bituminous mix with cellulose fiber and stone dust and lime stone as filler and found its suitability as SMA mix through various tests.[5]

Punith V.S., Sridhar R., Bose Sunil, Kumar K.K., Veeraragavan A (2004) did a comparative study of SMA with asphalt concrete mix utilizing reclaimed polythene in the form of LDPE carry bags as stabilizing agent (3 mm size and 0.4%). The test results indicated that the mix properties of both SMA and AC mixture are getting enhanced by the addition of reclaimed polythene as stabilizer showing better rut resistance, resistance to moisture damage, rutting, creep and aging.

Muniandy R., Huat, B.B.K. (2006) used Cellulose oil palm fiber (COPF) and found fiber- modified binder showed improved rheological properties when cellulose fibers were preblended in PG64-22 binder with fiber proportions of 0.2%,0.4%,0.6%,0.8 % and 1.0% by weight of aggregates. It showed that the PG64-22 binder can be modified and raised to PG70- 22 grade. The Cellulose oil palm fiber (COPF) was found to improve the diametral fatigue performance of SMA design mix. The fatigue life increased to a maximum at a fiber content of about 0.6%, whilst the tensile stress and stiffness also showed a similar trend in performance. The initial strains of the mix were lowest at a fiber content of 0.6%.[10]

Kumar Pawan, Chandra Satish and Bose Sunil (2007) tried to use an indigenous fiber in SMA Mix by taking low viscosity binder coated jute fiber instead of the traditionally used fibers and compared the result with the imported cellulose fiber, using 60/70 grade bitumen and found optimum fiber percentage as 0.3% of the mixture. Jute fiber showed equivalent results to imported patented fibers as indicated by Marshall stability test, permanent deformation test and fatigue life test. Aging index of the mix prepared with jute fiber showed better result than patented fiber.[12]

Shaopeng Wu et al. (2007) used slag after 3 year of ageing with PG76-22 modified binder, lime stone filler, short chopped polyester fiber (3%) for the SMA mix in Marshall method and found it to be suitable for use.[13]

Chui-Te Chiu, Li-Cheng Lu, (2007) used asphalt rubber (AR), produced by blending ground tire rubber (GTR) (i)

30% of a coarse GTR with a maximum size of #20 sieve and (ii)20% of a fine with a maximum size of #30 sieve with an asphalt, as a binder for SMA and found AR-SMA mixtures were not significantly different from conventional SMA in terms of moisture susceptibility and showed better rutting resistance than that of conventional dense graded mixture.[11]

Yongjie Xue, Haobo Hou, Shujing Zhu, Jin Zha (2008) used municipal solid waste incinerator (MSWI) fly ash as a partial replacement of fine aggregate or mineral filler and BOF Slag as part of coarse aggregate with polyester fiber of 6.35 mm in length obtained from recycled raw materials, PG76-22 binder in the SMA mix and performed Marshall and super pave method of design and found its suitability for use in the SMA mix.[15]

Vasudevan et al [2014], exhibited an investigation on the readiness of plastics squander – bitumen mix and its properties to discover the appropriateness of the mix for street development, was completed. A changed procedure was produced and the stone total was covered with liquid plastics and the plastics squander covered total (PCA) was utilized as the crude material for adaptable development. PCA demonstrated better restricting property. It had less wetting property. Its voids were substantially less. The example demonstrated higher Marshall Solidness esteem. The streets laid utilizing PCA are performing admirably. A point by point considered is exhibited.

Vasudevan, et al. [2015] likewise watched that the polymer mixed bitumen has better properties with respect to Softening point, Entrance point, Flexibility, Stripping Quality and Marshall Security esteem. Thus the mix can be utilized for laying adaptable asphalt. In this investigation both dry and wet procedures were utilized to get ready adjusted bituminous blends. In the wet procedure, the mixing was done by straightforwardly blending the destroyed polymer with hot bitumen at 160 deg. C. In the dry procedure, a novel system was utilized to utilize higher level of waste plastics in street development and utilizing this strategy a substitute technique was utilized. In this technique, the waste polymer was included the hot total (170deg.C). The polymer was covered over the total. Here the spreading was simple. The hot total was covered with polymer consistently. At that point the Bitumen was included. The blending of bitumen with polymer was occurring at the surface of the total. The temperature was around 155 – 163 C. Both the polymer and bitumen were in the fluid state.

Vasudevan et al [2016] displayed that plastic waste comprising of convey sacks, containers and thermocols can be utilized as a covering over total and this covered stone can be utilized for street development. By this procedure a street of 1 Km length and 3.375M width of single path can expend 10, 00000 convey sacks and the

street quality is expanded by 100% and there is no pot opening arrangement. Infiltration was diminished to a low esteem and correspondingly the pliability. It has been construed that the utilization of higher rate (over 3%) of plastics in polymer altered bitumen isn't good. The paper additionally contemplates utilization of scrap elastic waste as bitumen modifier. Squander tires are powdered and the powder is mixed with bitumen (80/100) warmed to 100-120oC and blended at speed of 3000 rpm for 2-3 hours. This mix is utilized alongside plastic covered total. The blend polymer covered total and tire altered bitumen have indicated higher quality. The level of scrap elastic modifier in the blend changes from 1% to 5%.

Yadav et al [2017] manages the improvement of changed fastener definitions from plastomer and elastomer waste squander with a mean to limit non-biodegradable the post customer polymer squander and also ecological peril, to meet this target ten unique examples have been grabbed from a few sorts of waste to cover distinctive classifications of polymeric waste from the household, mechanical and in addition therapeutic waste. Changed cover definitions were at first portrayed according to the pertinent gauges (code of training) to determining their appropriateness for above said application. The physical properties of altered covers are inside as far as possible. Marshall Soundness, backhanded rigidity and crawl modulus conduct have been assessed and talked about in this examination to demonstrate their double advantages like waste minimization and appropriateness of such fasteners to be utilized for sturdy street.

III. PROBLEM IDENTIFICATION

The growth in various types of industries together with population growth has resulted in enormous increase in economic activities world-wide.

- Various developments have caused tremendous increase in the movement of people and goods, causing much stress on roads.
- Road gets damaged frequently.
- Industrial developments & growth of population have resulted increase in economic activities.

Objectives

- Study of properties of SMA mix with banana fiber.

IV. CONCLUSION

By addition of 0.35% fiber to SMA, Stability value increases significantly, further addition to it stability decreases. Main advantage of using fiber is that air voids in mix decreased due to addition of banana fiber.

REFERENCES

- [1] Chui-Te Chiu, Li-Cheng Lu, "A Laboratory study on stone matrix asphalt using ground rubber", *Construction and Building Materials*, Volume 21, Issue 5, May 2007, Pages 1027-1033.
- [2] D-6926-04 ,Standard practice for preparation of Bituminous Specimens using Marshall Apparatus.
- [3] D-6927-06, Standard Test Method for Marshall Stability and Flow of Bituminous Mixtures.
- [4] Georgia Department of Transportation, 'Summary of Georgia's Experience with Stone Matrix Asphalt Mixes', 2003
- [5] H. Behbahani, S. Nowbakht, H. Fazaeli and J. Rahmani ,Effects of Fiber Type and Content on the Rutting Performance of Stone Matrix Asphalt, *Journal of Applied Science Year: 2009, Volume: 9, Issue 10, Page No. 1980-1984*
- [6] http://www.hawaiiasphalt.com/HAPI/modules/04_pavement_types/04_mix_types.htm#sma (visited on February 17, 2010).
- [7] <http://www.sisal.ws/page6/page7/page7.html>.
- [8] IS 2386 : Part I : 1963 (Reaffirmed 2002) ,Methods of Test for Aggregates for Concrete
- [9] Jared, David. GDOT Research Project 9102: Evaluation of Stone Matrix Asphalt and Porous European Mix. Georgia Department of Transportation, 1997.
- [10] Kumar Pawan, Chandra Satish and Bose Sunil, 'Laboratory investigations on SMA mixes with different additives', *International Journal of Pavement Engineering*, Volume 8, Issue1, March 2007, Pages11-18.
- [11] Manual for construction and supervision of bituminous works, MoRTH, IRC, New Delhi, 2001.